

# R 118 A101

## Applications

- ETICS
- Façade reinforcement

## Fabric Versions Available

- R 118 A101 C+, CSTB TRaME 2/1/4/3

## Dimensional characteristics

Square dimension warp/weft (mm)	9	10
Treated fabric weight (g/m <sup>2</sup> )	138	
Loom state fabric weight (g/m <sup>2</sup> )	118	
Treated fabric thickness (mm)	0,67	
Standard roll width/length (m)	1	50
Standard pallet no. of rolls	30	

## Chemical characteristics

Glass	E
Coating	alkali resistant
Combustion heat (MJ/kg)	7,6

## Mechanical characteristics

Tensile strength in standard conditions warp/weft (N/5 cm)	2050	2400
Elongation in standard conditions warp/weft (%)	3,5	3,5
Tensile strength after 28 days ETAG test warp/weft (%)	60	55

## Options Available

- Color adjustment: yes
- Fabric softness: D
- Logo print: yes
- Width: 20 cm – 100 cm
- Length: 50 m – 500 m



*Other options than mentioned to be checked with a product manager.*

## Quality Inspection

Quality inspection, sampling and material acceptance follows the Customer Acceptance Standard No. 0326.

## Packing

The rolls of fabrics are packed vertically in a cardboard box, on a wooden pallet. A precise method of packing is mentioned in the works standard for packing and can vary based on a customer request.

## Storing

Packed rolls are to be stored in dry rooms. Storing temperature is from -10 °C to +50 °C.





Vertex®

